



# REXILENT

## FLOOR PRODUCTS

Technical Data Sheet

Revised: 01/10/2018

### DESCRIPTION

Water-based acrylic adhesive for all types of PVC coverings, linoleum and resilient floorings.

- + Excellent open time
- + Strong hold final
- + Low C.O.V (Volatile Organic Compounds)
- + Antibacterial and anti-mold properties

Suitable for:

- floorings in homogeneous vinyl and PVC
- tiles and PVC carpet tiles
- polyester or polystyrene coatings
- linoleum floorings
- natural cork floorings or with PVC backing
- thermo-acoustic coatings

### SURFACE PREPARATION

All surfaces must be dry, absorbent, strong, free of dust or paints or oils. Any cracks must be sealed with our 2-component epoxy adhesive Epoxy. The support must have a humidity: for cement surfaces max. 3% - for the areas in anhydrite. 0.5%.

On rough roads, it recommends the use of self-leveling cement-based. To make the product effective even at low temperatures use our VISO-LYN ST100 as a percentage of 10% on the amount of smoothing.

We always recommend the use of our PRIMER AC fixative for consolidation and cleaning.

We recommend using our PRIMER SP (specific for wet floors with fungi and mold) in case of rising damp or too humid areas.

### COATING PREPARATION

Before proceeding with the laying of the covering it is recommended to take it at the construction site the day before in order to allow an adaptation to the environment temperature.

Lay the covering by following the instructions given by the manufacturer. Unroll or simply unpack the flooring to be laid in order to decrease tensions and folds..

### PRODUCT PREPARATION

REXILENT is a ready to use product.

### APPLICATION

SPATULA - Apply with a notched trowel No. 2 or No. 3 on the floor. Then proceed to the preparation of materials.

### CONSUMPTION

250 - 350 g/m<sup>2</sup>

### CLEANING

We recommend to clean the joints and excess adhesive with a wet sponge. Any adhesive spillage must be removed immediately. The product does not stain.

### CONTRAINDICATIONS

- + Do not use for outdoor applications (using Adhesiva 2P/G).
- + Do not use at temperatures below + 3 ° C
- + Do not use on damp or subject to rising damp
- + Treat non-absorbent surfaces to make them porous.

### PACKAGES

bucket 6 Kg  
bucket 13 Kg  
bucket 20 Kg

code 20023  
code 20024  
code 20025

### STORAGE

The product is guaranteed for 24 months from the date of production. Preserve from frost. (+ 5 °C + 40 °C)

### TECHNICAL DATA

base:	water
appearance:	white cream
pH:	6.8
viscosity:	45,000 to 55,000 cps
c.o.v.:	<0.05 g/m <sup>3</sup>
percentage of solid:	70%
customs code:	3506 9190
application temperature:	+ 5 °C + 40 °C
waiting time:	15 - 20 minutes
open time:	30 - 40 minutes
setting time:	24 hours
non flammable	

### FINAL REGULATIONS

Keep out of the reach of children and pets. Discharge the waste in special containers for building materials.



A.C.M. Sas di Danese R. & C. | Via XXV Aprile, 62 | 20010 Bareggio /MI  
PHONE +39 02 903 611 48 | laboratorio@acm-italy.com | www.acm-italy.com